CONFIDENTIAL

CENTRAL INTELLIGENCE AGENCY   REPORT

INFORMATION REPORT

CD NO.   25X1

COUNTRY	USSR	DATE DISTR. 31 Mar 1950
SUBJECT	Character of Composition vs Property Curves of Metallurgical Solid Solutions at High Temperatures	NO. OF PAGES 1
25X1 PLACE ACQUIRED		NO. OF ENCLS. (LISTED BELOW)
DATE ACQUIRED		SUPPLEMENT TO REPORT NO. 25X1
DATE OF		

THIS IS UNEVALUATED INFORMATION

25X1

translation of an article entitled "On Character of Composition vs Property Curves of Metallurgical Solid Solutions at High Temperatures" by A M Borzdyka which appeared in "Doklady Akademii Nauk SSSR", Vol 65, 1949, No 4, at pages 505-507. This article contains a study of applicability of relationships established for atmospheric temperature between chemical composition and properties of solid solution alloys to conditions prevailing in high temperature service. Alloys studied: Fe-Ni; Fe-Cr-Ni, also Fe-Cr-Mn. Properties studied: Creep strength, hardness, conductivity - Conclusions to be drawn.

25X1

-end-

				DISTRIBUTION							
STATE	X NAVY	X NSRB									
ARMY	X AIR	X FBI									

4. M. Furz ... a:

ON THE CHARACTER OF COMPOSI-
TION VS. PROPERTY CURVES OF
METALLURGICAL SOLID SOLUTIONS
AT HIGH TEMPERATURES.

ILLEGIB

Figure 1. Alloys of Fe-Ni
system.

Figure 2. Austenitic alloys
of ternary Fe-Cr-Ni system
(section containing 20% chro-
mium).

Figure 3. Austenitic alloys
of ternary Fe-Cr-Ni system
(section containing 20% chro-
mium).

ON CHARACTER OF COMPOSITION VS. PROPERTY CURVES

OF METALLURGICAL SOLID SOLUTIONS

AT HIGH TEMPERATURES

By A. M. Borzdyka

S y n o p s i s.

Study of applicability of relation-
ships established for atmospheric
temperature between chemical com-
position and properties of solid
solution alloys to conditions
prevailing in high temperature
service.

Alloys studied: Fe-Ni; Fe-Cr-Ni,
also Fe-Cr-Mn. Properties studied:
Creep strength, hardness, conduct-
ivity.- Conclusions to be drawn.

Practical application of the alloys distinguished
by their high strength at elevated temperatures, many of which
belong to the class of solid solutions as regards their struc-
ture, requires a knowledge of their mechanical and physical
properties at the temperatures to which they are exposed in
service.

However, systematic study of the properties of metallic solid solutions as a function of their chemical composition has until recently been more or less confined to the range of atmospheric temperatures.

Extrapolation of such values into the range of high temperatures is impossible. Quite apart from the sharp difference between the numerical values of the various properties for ordinary temperature and those for elevated temperatures, the very character of the variation in these properties at high temperatures as a function of the composition may differ profoundly from the relationships established for ordinary temperatures.

Still, the initiator of the composition-property diagrams, N. S. Kurnakov ventured the hypothesis that "by analogy to liquid solutions, increased temperatures are bound to flatten out the isotherms of the properties and displace the minimum point (on the electrical conductivity curve) in the direction of the component having the lower conductivity. Under the same conditions, the maximum of the hardness will be shifted in the direction of the harder component of the alloy." [1]

For a long time, these statements were without confirmation by experiment. To-day, however, it may be regarded as established that increased temperatures diminish the curvature of the composition-property curves and produce a flattening (and sometimes, complete disappearance) of the maximum or minimum point, holding for atmospheric temperature.

To give an example, a set of isotherms of the electrical

conductivities (at temperatures ranging from 0 to 1000° C) is
presented in Figure 1 for the alloys of the binary system Fe-Ni,
which is known to form a structure of uniform γ solid solution.
The flattening of the curves with increasing temperature is still
more pronounced on the electrical conductivity curves of the alloys
of the ternary system Fe-Cr-Ni (cross section for 20% Cr; Fig. 2).

When comparing the curves of Figure 2 with those of
Figure 1, the differences in the curvature and the position of
the maximum, which latter is absent entirely from the 800° C
(1470° F) isotherm, are apparent. This confirms the fact that
the properties of ternary systems forming solid solutions do
not always vary according to the rules established for binary
systems.[3]

It is natural to assume that a flattening of the
composition-property curves with increasing temperatures may
take place also in the case of the properties characterizing
high temperature strength of a metallic alloy, meaning the
capacity to retain a sufficient amount of mechanical strength
at elevated temperatures.

The results of hardness determinations on alloys of
the Fe-Cr-Ni system (20% Cr cross section) at temperatures
ranging from 20 to 700° C (68-1290° F) have been plotted in
Figure 3 against the nickel content.

The gradual disappearance of the maximum from the
curves, as the temperature goes up, is evident. The tests
made at a temperature of 700° C (1290° F) give an almost
straight line.

The basic property which governs the high temperature strength of a metal or alloy is the creep resistance. As has been shown in an earlier paper by the author,[4] the isotherms of the "limiting creep stress", as a function of the nickel content, for the same cross section of the ternary system Fe-Cr-Ni also show a rectilinear character at temperatures of 600 and 700° C (1110 and 1290° F), analogously to the isotherms of Figure 3. A similar picture is offered by the isotherms of creep for the austenitic alloys of the Fe-Cr-Mn system.

All of these facts constitute proof that the classic concept of the variation of the properties of solid solutions as a function of their composition, which is true of atmospheric and moderately high temperatures, does not apply to elevated temperatures.

R e f e r e n c e s:

(1) N. S. Kurnakov, "Introduction to Physical-Chemical Analysis", (Book, in Russian), 1940, p. 121;

(2) T. Yensen, JOURNAL FRANKLIN INSTITUTE, vol. 199, 1925, p. 333;

(3) V. A. Nemilov and T. A. Vidusova, IZVESTIYA SEKTORA PLATINY IONKh AN SSSR, vol. 17, 1940, p. 111;

(4) A. Borzdyka, DOKLADY AKADEM. NAUK SSSR, vol. 63, 1947, No. 3 (sic!).

25X1